

1: Identification of the substance/Preparation and company

1.1 PRODUCT IDENTIFICATION

PRODUCT NAME: AP2469 Acrylic Paint 24colors

USE OF PRODUCT: Paint by artist, amateur and students

COLOR : Titanium White、Lemon Yellow、Yellow Deep、Yellow Mid、Yellow Ochre、Orange、Magenta、Vermilion、Scarlet、Crimson、Sap Green、Phthalo Green、Viridian、Monastral Green、Cerulean Blue、Phthalo Blue、Deep Cyan Blue、Purple、Raw Sienna、Burnt Sienna、Burnt Umber、Lamp Black、Gold、Silver

COMPANY DETAILS:

NAME: Tianchang Jiafeng Painting Material Co., Ltd

ADDRESS: Shizhuang Village, Zhengji Town, Tianchang City, Anhui Province, China

TEL: +86-550-7964322

FAX: +86-550-7964422

CONTACT PERSON: Chen Feng

EMAIL ADDRESS: Chen-feng@jabp.com

1.2 EMERGENCY TELEPHONE

TEL: +86-550-7964322

2. Hazard identification

2.1. Classification of the mixture

The substance is not classified according to the Globally Harmonized System (GHS).

2.2. Label elements

The products does not have to be labeled .

3. Composition/information on ingredients

COMPOSITION	CAS NO	PERCENTAGE
1.Titanium White		
Water	7732-18-5	42.698%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.420%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	22.960%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.020%
Calcium carbonate	471-34-1	14.000%
Titanium dioxide (P.W.6)	13463-67-7	18.000%
2.Lemon Yellow		
Water	7732-18-5	51.698%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.480%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%

N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	22.960%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.080%
Calcium carbonate	471-34-1	15.250%
2-[(4-Chloro-2-nitrophenyl)azo]-N-(2-chlorophenyl)-3-oxobutyramide(P.Y.3)	6486-23-3	7.630%
3. Yellow Deep		
Water	7732-18-5	48.252%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.440%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	22.660%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	0.960%
Calcium carbonate	471-34-1	18.180%
4,4'-[(3,3'-dichloro{1,1'-biphenyl}-4,4'-diyl)bis(azo)]bis[2,4-dihydro-5-methyl-2-phenyl-3H-pyrazol-3-one](P.O.13)	3520-72-7	0.580%
2-[(4-Methyl-2-nitrophenyl)azo]-3-oxo-N-phenylbutanamide(P.Y.1)	2512-29-0	8.026%
4. Yellow Mid		
Water	7732-18-5	54.328%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.420%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	23.820%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.010%
Calcium carbonate	471-34-1	15.360%
2-[(4-Methyl-2-nitrophenyl)azo]-3-oxo-N-phenylbutanamide(P.Y.1)	2512-29-0	4.1600%
5. Yellow Ochre		
Water	7732-18-5	49.200%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.408%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%

N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	23.360%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.140%
Calcium carbonate	471-34-1	11.660%
Iron hydroxide oxide (P.Y.42)	51274-00-1	13.330%
6.Orange		
Water	7732-18-5	50.214%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.415%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	22.269%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.200%
Calcium carbonate	471-34-1	20.000%
4,4'-[(3,3'-dichloro{1,1'-biphenyl}-4,4'-diyl)bis(azo)]bis[2,4-dihydro-5-methyl-2-phenyl-3H-pyrazol-3-one](P.O.13)	3520-72-7	5.000%
7.Magenta		
Water	7732-18-5	54.184%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.430%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	22.365%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.074%
Calcium carbonate	471-34-1	18.375%
5,12-dihydro-2,9-dimethylquino[2,3-b]acridine-7,14-dione(P.R.122)	980-26-7	2.670%
8.Vermilion		
Water	7732-18-5	54.158%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.420%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	22.130%

2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.090%
Calcium carbonate	471-34-1	16.000%
Pyrrolo[3,4-c]pyrrole-1,4-dione, 3,6-bis(4-chlorophenyl)-2,5-dihydro- (P.R.254)	84632-65-5	1.300%
2-[(4-Chloro-2-nitrophenyl)azo]-N-(2-chlorophenyl)-3-oxobutyramide(P.Y.3)	6486-23-3	4.000%
9.Scarlet		
Water	7732-18-5	50.758%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.450%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	22.530%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.030%
Calcium carbonate	471-34-1	18.330%
Pyrrolo[3,4-c]pyrrole-1,4-dione, 3,6-bis(4-chlorophenyl)-2,5-dihydro- (P.R.254)	84632-65-5	6.000%
10.Crimson		
Water	7732-18-5	51.653%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.425%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	23.320%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.150%
Calcium carbonate	471-34-1	19.300%
calcium 3-hydroxy-4-[(4-methyl-2-sulphonatophenyl)azo]-2-naphthoate (P.R.57:1)	5281-04-9	3.250%
11.Sap Green		
Water	7732-18-5	47.776%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.412%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	23.080%

2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.030%
Calcium carbonate	471-34-1	20.690%
29H,31H-phthalocyaninato(2-)-N29,N30,N31,N32 copper (P.B.15)	147-14-8	0.950%
2-[(4-Methyl-2-nitrophenyl)azo]-3-oxo-N-phenylbutanamide(P.Y.1)	2512-29-0	5.160%
12. Phthalo Green		
Water	7732-18-5	49.350%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.405%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	22.380%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.133%
Calcium carbonate	471-34-1	20.000%
Polychloro copper phthalocyanine(P.G.7)	1328-53-6	5.830%
13. Viridian		
Water	7732-18-5	49.648%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.402%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	22.210%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.168%
Calcium carbonate	471-34-1	16.670%
Polychloro copper phthalocyanine(P.G.7)	1328-53-6	6.000%
Titanium dioxide (P.W.6)	13463-67-7	3.000%
14. Monastral Green		
Water	7732-18-5	55.018%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.480%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	21.090%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.210%

Calcium carbonate	471-34-1	15.000%
Polychloro copper phthalocyanine(P.G.7)	1328-53-6	0.600%
2-[(4-Chloro-2-nitrophenyl)azo]-N-(2-chlorophenyl)-3-oxobutyramide(P.Y.3)	6486-23-3	5.700%
15.Cerulean Blue		
Water	7732-18-5	48.028%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.440%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	24.380%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.210%
Calcium carbonate	471-34-1	11.670%
29H,31H-phthalocyaninato(2-)-N29,N30,N31,N32 copper (P.B.15:3)	147-14-8	1.500%
Polychloro copper phthalocyanine(P.G.7)	1328-53-6	0.200%
Titanium dioxide (P.W.6)	13463-67-7	11.670%
16.Phthalo Blue		
Water	7732-18-5	48.784%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.414%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	22.680%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.220%
Calcium carbonate	471-34-1	20.000%
29H,31H-phthalocyaninato(2-)-N29,N30,N31,N32 copper (P.B.15:3)	147-14-8	6.000%
17.Deep Cyan Blue		
Water	7732-18-5	53.248%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.500%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	22.000%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.050%

Calcium carbonate	471-34-1	15.000%
29H,31H-phthalocyaninato(2-)-N29,N30,N31,N32 copper (P.B.15:3)	147-14-8	3.600%
Titanium dioxide (P.W.6)	13463-67-7	3.700%
18.Purple		
Water	7732-18-5	47.821%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.431%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	22.312%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.214%
Calcium carbonate	471-34-1	25.090%
8,18-dichloro-5,15-diethyl-5,15-dihydrodiindolo[3,2-b:3',2'-m]triphenodioxazine(P.V.23)	215247-95-3	2.230%
19.Raw Sienna		
Water	7732-18-5	46.818%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.500%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	22.000%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.080%
Calcium carbonate	471-34-1	15.000%
Iron hydroxide oxide (P.Y.42)	51274-00-1	13.000%
Iron hydroxide oxide red (P.R.101)	1309-37-1	0.700%
20.Burnt sienna		
Water	7732-18-5	46.442%
2-amino-2-methylpropanol	124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether	9004-58-4	0.436%
2-phenoxyethanol	122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one	4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine	2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene	25085-34-1	23.120%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate	25212-88-8	1.320%
Calcium carbonate	471-34-1	23.010%
Iron hydroxide oxide (P.Y.42)	51274-00-1	2.150%
Iron hydroxide oxide red (P.R.101)	1309-37-1	2.620%

21.Burnt Umber			
Water		7732-18-5	50.846%
2-amino-2-methylpropanol		124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether		9004-58-4	0.402%
2-phenoxyethanol		122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one		4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine		2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene		25085-34-1	22.130%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate		25212-88-8	1.090%
Calcium carbonate		471-34-1	18.180%
Iron hydroxide oxide (P.Y.42)		51274-00-1	2.580%
Iron hydroxide oxide red (P.R.101)		1309-37-1	3.770%
Carbon Black (P.BK.7)		1333-86-4	0.100%
22.Lamp Black			
Water		7732-18-5	64.132%
2-amino-2-methylpropanol		124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether		9004-58-4	0.436%
2-phenoxyethanol		122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one		4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine		2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene		25085-34-1	25.580%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate		25212-88-8	0.810%
Carbon Black (P.BK.7)		1333-86-4	8.140%
23.Gold			
Water		7732-18-5	63.898%
2-amino-2-methylpropanol		124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether		9004-58-4	0.600%
2-phenoxyethanol		122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one		4299-07-4	0.001%
N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine		2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene		25085-34-1	22.000%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate		25212-88-8	0.600%
Golden Powder	Mica (55%)	12001-26-2	12.000%
	TiO ₂ (36%)	13463-67-7	
	Fe ₂ O ₃ (9%)	1309-37-1	
24.Silver			
Water		7732-18-5	61.458%
2-amino-2-methylpropanol		124-68-5	0.400%
Cellulose, ethyl 2-hydroxyethyl ether		9004-58-4	0.600%
2-phenoxyethanol		122-99-6	0.500%
2-n-butyl-benzo[d]isothiazol-3-one		4299-07-4	0.001%

N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine		2372-82-9	0.001%
2-Propenoic acid, polymer with ethenylbenzene		25085-34-1	22.000%
2-Propenoic acid, 2-methyl-, polymer with ethyl 2-propenoate		25212-88-8	0.600%
Silver White Powder	Mica (55%)	12001-26-2	14.000%
	TiO ₂ (45%)	13463-67-7	
Iron hydroxide oxide Black (P.BK.11)		1317-61-9	0.440%

4. First aid measures

4.1 Description of first aid measures

After skin Contact: If skin or hair contact occurs, Flush skin and hair with running water (and soap if available). Seek medical attention in event of irritation.

After eye Contact: If this Product comes in contact with eyes: Wash out immediately with water. If irritation continues, seek medical attention. Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.

After ingestion: Immediately give a glass of water. First aid is not generally required. If in doubt, contact a Poisons Information Centre or a doctor.

After inhalation: If fumes, aerosols or combustion products are inhaled, remove from contaminated area. Other measures are usually unnecessary.

4.2 Most important symptoms and effects, both acute and delayed.

No data available

4.3. Indication of any immediate medical attention and special treatment needed:

Information not available.

5. Fire fighting Measures

5.1 Suitable Extinguishing Media	There is no restriction on the type of extinguisher which may be used. Use extinguishing media suitable for surrounding area.
5.2 Combustion products and resulting gases	Carbon monoxide (CO) carbon dioxide (CO ₂) other pyrolysis products typical of burning organic material.
5.3 Special Protective Equipment	Avoid contamination with oxidising agents i.e. nitrates, oxidising acids, chlorine bleaches, pool chlorine etc. as ignition may result.

6. Accidental release Measures

6.1 Personal Protection	Clean up waste regularly and abnormal spills. Avoid breathing dust and contact with skin and eyes. Wear protective clothing, gloves, safety glasses and dust respirator. Use dry clean up procedures and avoid generating dust.
6.2 Environmental Protection	Not applicable
6.3 Methods for cleaning up	Not applicable
6.4 Reference to other sections	Any information on personal protection and disposal is given in sections 8 and 13.

7. Handling and storage

7.1 Handling Precautions	Store in cool, dry place in tightly closed receptacles. Keep ignition source away – Do not smoke.
7.2 Storage Precautions	Store in a cool location. Store away from flammable substances.
7.3 Specific end use(s)	Information not available.

8. Exposure controls/personal protection

8.1 Respiration Protection	Not required.
8.2 Hand Protection	The glove material has to be impermeable and resistant to the products/the substance/the preparation. Due to missing test no recommendation to the glove material can be given for the product/the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rate of diffusion and the degradation
8.3 Eye Protection	Not required
8.4 Skin Protection	Generally the product does not irritate the skin. If skin or hair contact occurs, Flush skin and hair with running water (and soap if available)

9. Physical and chemical properties

Appearance	Paste	Auto flammability	Product is not self igniting.
Color	24 colors	Explosive properties	Product does not present explosion hazard
Odour	No	Oxidizing properties	Not available
PH	8.0-9.0	Vapor pressure	Not available
Boiling point/boiling range	Not available	Relative density	1.08-1.32 g/cm ³
Melting point/melting range	Not available	Solubility in water	NO (after dry)
Flash point	> 100°C	Partition coefficient	Not available
Flammability	No	Others	No

10. Stability and reactivity

10.1. Reactivity.	There are no particular risks of reaction with other substances in normal conditions of use.
10.2. Chemical stability.	The product is stable in normal conditions of use and storage
10.3. Possibility of hazardous reactions.	No hazardous reactions are foreseeable in normal conditions of use and storage.
10.4. Conditions to avoid	None in particular. However the usual precautions used for chemical products should be respected.
10.5. Incompatible materials	Information not available.

10.6. Hazardous decomposition products	No
---	----

11. Toxicological information

11.1Inhalation	No significant effects expected from a single short-term exposure.
11.2Ingestion	Low ingestion hazard in normal use.
Skin contact	No significant irritation expected from a single short-term exposure.
11.3Eye contact	Direct contact may cause temporary redness and discomfort
11.4Carcinogenicity	No data available
11.5Other	No

12. Ecological information

12.1. Toxicity.	Information not available
12.2. Persistence and degradability	Information not available
12.3. Bioaccumulative potential.	Information not available
12.4. Mobility in soil	Siloxanes are removed from water by sedimentation or binding to sewage sludge.
12.5. Results of PBT and vPvB assessment	On the basis of available data, the product does not contain any PBT or vPvB
12.6. Other adverse effects	Information not available

13. Disposal considerations

13.1Methods of disposal	Do not allow wash water from cleaning or process equipment to enter drains.
13.2Dangers in disposal	No

14. Transport information

Transportation Status: Important! Statements below provide additional data on listed Dot classification.

The listed Transportation Classification does not address regulatory variations due to changes in package size, mode of shipment or other regulatory descriptors.

US Department of Transportation

Shipping Name: IMDG NOT REGULATED

14.1UN number	No
14.2UN proper shipping name	No
14.3Transport hazard class(es)	No
14.4Packing group	Unregulated
14.5Environmental hazards	No
14.6Special precautions for user	No

14.7Transport in bulk
according to Annex II of
MARPOL73/78 and the
IBC Code

Unregulated

15. Regulatory information

15.1: *Chemical safety assessment*

NO

15.2: *Chemical safety assessment*

NO

16. Other information

The information in this MSDS was obtained from sources which we believe are reliable . However , the information is provided without any warranty ,express or implied , regarding its correctness . The conditions or methods of handling ,storage , use or disposal of the product are beyond our control and may be beyond our knowledge . For this and other reasons , we do not assume responsibility and expressly disclaim liability for loss , damage or express arising out of or in any way connected with the handling , storage , use or disposal of the product . This MSDS was prepared and is to be used only for this product . If the product is used as a component in another product , this MSDS information may not be applicable.

.***** END of document