

Weight (g/m2, +/-5%)	360	
Thickness (mm +/-5%)	0.8	
Roll Width (cm, +/-2%)	144	
Group	Artificial Leather PU	
Treatment		
Raw material composition	66% PU, 30% PES, 1.3% CV, 2.7% COT 66% PU, 30% PES, 1.3% CV, 2.7% COT	
Colour fastness to light	4	1-5, 1= bad, 5= good
Colour fastness to rubbing	4-5 4-5	1-5, 1= bad, 5= good
Martindale test	>100,000	
Tearing strenght (N)	37 29	
Tensile Strenght (N)	550 490	
Pilling resistance	4-5	1-5, 1= bad, 5= good
Seam slilage (mm)	1.7 2.1	acceptable <4, 1= is greate
Care instructions	    	